



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 877 063 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
26.03.2003 Bulletin 2003/13

(51) Int Cl.7: C09D 7/02, C08G 69/34,
B01F 17/00, C09D 5/02

(21) Application number: 98108063.3

(22) Date of filing: 04.05.1998

(54) Antisettling agent for aqueous paints

Antiabsetzmittel für wässrige Lacke

Agents de suspension pour compositions aqueuses de revêtement

(84) Designated Contracting States:
DE ES FR GB IT

(30) Priority: 09.05.1997 JP 13592697

(43) Date of publication of application:
11.11.1998 Bulletin 1998/46

(73) Proprietor: Kusumoto Chemicals, Ltd.
Chiyoda-ku, Tokyo (JP)

(72) Inventor: Wakui, Toshimitsu
Soka-shi, Saitama-ken (JP)

(74) Representative:
Weisert, Annekäte, Dipl.-Ing. Dr.-Ing. et al
Patentanwälte
Kraus & Weisert
Thomas-Wimmer-Ring 15
80539 München (DE)

(56) References cited:
DE-A- 4 028 386 US-A- 5 374 687

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 877 063 B1

Description

[0001] This invention relates to an antisetling agent for aqueous paints which, when added, for example to an aqueous metallic paint, an aqueous corrosion-resistant paint or the like, prevents the settling of the pigment in the aqueous paint, without spoiling the sharpness and water resistance of the paint film.

[0002] Aluminum pigments or pearlescent pigments such as mica used in metallic paints, or corrosion-resistant pigments used in corrosion-resistant paints are such that the particle size of the pigment is large and the specific gravity thereof is also large, and therefore, settling readily occurs in paints. It is well-known that, in solvent type paints, amide wax type or polyethylene oxide wax type antisetling agents are used for preventing settling, but many of these additives are unsuitable for use in aqueous paints.

[0003] As antisetling agents for aqueous paints are proposed inorganic antisetling agents such as clay series ones shown in "Toso Gijutsu, 35(6), 82-83 (1996)" and "Toso Gijutsu, 35(6), 84-85 (1996)" or silica series ones shown in "Toso to Toryo, No. 494(7), 49-52 (1992)". However, these inorganic additives have defects, e.g. that they cause the lowering of luster or they are hard to add after the preparation of paints.

[0004] Further, it is disclosed in Japanese Laid-open Patent Publication No. 234461/1992 that by using hydrophilic colloidal silica and, as a surfactant, a water-soluble or water dispersible nonionic fluorinated hydrocarbon polymer containing ethylene oxide linkage, it is possible to retard the settling of the pigments in metallic paints and improve the stability and performance of the paints. However, since an inorganic silica is used, there is a problem of dust.

[0005] In U.S. Patent No. 5,374,687, a substance obtained by neutralizing with a neutralizing agent an emulsifying copolymer obtained from an α -olefin and an α,β -ethylenic unsaturated carboxylic acid is shown as an aqueous antisetling agent. This additive is liquid and thus has an advantage on handling, but it is insufficient in effect as an antisetling agent for aluminum pigments or pearlescent pigments such as mica used in aqueous metallic paints. It is described in the description of the prior art of the patent that there are, as antisetling agents for aqueous paints, emulsifying polyethylene waxes, fumed silica, clay, natural gum, cellulosa derivatives, acrylic acid-acrylic ester copolymers, derivatives of reaction products of an unsaturated alcohol and an ethylenedicarboxylic acid, waxes, etc.

[0006] In recent years, examination of aqueous paints has actively been made because of environmental problems, danger of fires, etc., and also on antisetling agents, aqueous ones are naturally sought. Although, as stated above, various ones have hitherto been proposed as aqueous antisetling agents, they have had problems, e.g. that they are insufficient in effect to prevent the settling of pigments having large particle sizes and large specific gravities, for example, aluminum pigments and pearlescent pigments such as mica used in aqueous metallic paints, corrosion-resistant pigments used in aqueous corrosion-resistant paints, luster is lowered, water resistance is lowered.

[0007] In search of novel antisetling agents for aqueous paints to resolve such problems, the present inventor has succeeded in finding an antisetling agent for aqueous paints which prevents the settling of pigments used in aqueous metallic paints or aqueous corrosion-resistant paints and has almost no influence on the luster and water resistance of the paint film, and have come to complete the present invention. Namely, the invention aims to provide an antisetling agent for aqueous paints which gives excellent settling-preventing properties to aqueous paints and has little bad influence on the physical properties of paint film.

[0008] The antisetling agent for aqueous paints of the invention is obtained by neutralizing with a neutralizing base a polyamide obtained by reacting a carboxylic acid with a diamine, and then dispersing the neutralized polyamide in a medium mainly composed of water.

[0009] More specifically, by the present invention is provided an antisetling agent for aqueous paints obtained by neutralizing a polyamide, which is obtained by reacting a primary diamine having 2 to 12 carbon atoms with, in an amount excess to the diamine, a dimer dicarboxylic acid obtained by polymerizing an unsaturated fatty acid (common name: dimer acid) or a mixture of a dimer acid with another dicarboxylic acid having 3 to 21 carbon atoms and/or a monocarboxylic acid having 2 to 22 carbon atoms, with a neutralizing agent, and then dispersing the neutralized polyamide in a medium mainly composed of water.

[0010] Dimer acids used in the invention can be obtained by dimerizing unsaturated fatty acids, and ones generally put on the market can be used. Although monomer acids and trimer acids are contained besides dimer acids in dimer acids on the market, ones having a high dimer acid content are preferred.

[0011] In polyamides in the invention, dimer acids are used as carboxylic acids, but dicarboxylic acids other than dimer acids or monocarboxylic acids can be used together. As dicarboxylic acids, there can be used higher dicarboxylic acids having 21 or less carbon atoms besides succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, dodecanedioic acid, isophthalic acid, etc. As monocarboxylic acids, there can be used acetic acid, butyric acid, caproic acid, caprylic acid, capric acid, lauric acid, myristic acid, palmitic acid, stearic acid, behenic acid, 12-hydroxystearic acid, oleic acid, etc.

[0012] As carboxylic acids in the polyamides, dimer acids may be used solely, but dimer acids can also be used as mixtures with other dicarboxylic acids and/or monocarboxylic acids. When mixed carboxylic acids are used, compounding is made so that the mole ratio of the dimer acid contained in the total carboxylic acids may be 50 % or more. When

the mole ratio of the dimer acid is less than 50 %. sufficient settling-preventing effect is not obtained or the preparation of stable additives gets to be difficult.

[0013] As examples of primary diamines used in the invention, there can be used ethylenediamine, 1,4-diaminobutane, hexamethylenediamine, 1,10-decamethylenediamine, 1,11-undecamethylenediamine, 1,12-dodecamethylenediamine, xylylenediamine, 4,4'-diaminodiphenylmethane, etc.

[0014] The mole ratio of the total carboxylic acids to the primary diamine is made to be in the range of 5:4 to 2:1. When the amount of the total carboxylic acids is smaller than the mole ratio of the total carboxylic acids to the primary diamine being 5:4, the preparation of stable antisetling agents becomes difficult, or settling-preventing effect is lowered. On the other hand, when the amount of the total carboxylic acids is larger than the mole ratio of the total carboxylic acids to the primary diamine being 2:1, it becomes a cause of the lowering of the water resistance of paint film, or in some paints, gel structure having roping properties is formed when the resultant antisetling agents are compounded thereinto.

[0015] As the polyamide in the invention, one having an acid value in the range of 30 to 120 is used. Preferably used is one having an acid value of 40 to 100, and more preferably used is one having an acid value of 50 to 90.

[0016] The reaction of an above-mentioned primary diamine with a dimer acid or a mixture of a dimer acid with another dicarboxylic acid and/or a monocarboxylic acid, in an excess amount to the diamine, for the synthesis of the polyamide in the invention, can be carried out in a process well-known by persons skilled in the art. For example, the reaction can be carried out by reacting a mixture of the diamine with the carboxylic acid at a temperature of 150 to 200°C for 3 to 5 hours, and in this occasion, a dehydration ald such as xylene can, if necessary, be used.

[0017] A polyamide obtained by the above process has little crystallinity but is a solid at room temperature. According to the invention, this polyamide is dispersed in a medium mainly composed of water.

[0018] As methods to disperse the polyamide uniformly in the medium, there are a method to carry out the dispersion in one stage and a method to carry out the dispersion in two stages. The method to carry out the dispersion in one stage is a method which comprises neutralizing the synthesized polyamide with a neutralizing base at a temperature of 70 to 140°C, and then, if necessary after a proper organic solvent is added to lower the viscosity of the polyamide salt, adding the mixture into warm water under stirring. In the method to carry out the dispersion in two stages, the synthesized polyamide is neutralized with a neutralizing base at a temperature of 70 to 140°C, and, if necessary after a proper organic solvent is added to lower the viscosity of the polyamide salt, cooling the mixture once to room temperature, and then heating the, generally solid, polyamide salt or polyamide salt mixture cooled to room temperature to 70 to 140°C to make it liquid, and adding it into warm water under stirring to disperse it.

[0019] It depends on productive efficiency and equipment whether, when the polyamide is dispersed in a medium, the one-stage method is used or the two-stage method is used, and when any of the methods is used, the performance of the resultant antisetling agent is not influenced.

[0020] As neutralizing bases used for the neutralization of the polyamide, there can be used bases generally used as neutralizing bases in aqueous paints. There can, for example, be mentioned amines such as triethylamine and 2-dimethylaminoethanol, and inorganic bases such as sodium hydroxide and potassium hydroxide.

[0021] The polyamide salt formed by neutralizing the polyamide with a base can be dispersed as such in warm water, but it is also possible to add an organic solvent to lower the viscosity of the polyamide salt and then disperse the mixture into warm water. The purpose of lowering the viscosity of the polyamide salt is to facilitate the handling and facilitate the dispersion into warm water.

[0022] As organic solvents used for the above purpose, there can be mentioned aliphatic hydrocarbons, alicyclic hydrocarbons and aromatic hydrocarbons or mixtures thereof, ketones, esters, alcohols, ethers, etc., but organic solvents used in aqueous paints are preferred, and for example, propylene glycol monomethyl ether is mentioned.

[0023] The temperature of the polyamide salt or polyamide salt mixture to be dispersed in warm water is suitably 70 to 140°C. At temperatures lower than 70°C, the viscosity of the polyamide salt or polyamide salt mixture becomes high and it becomes hard to handle. When it is used at temperatures higher than 140°C, it becomes a cause of foaming when added into warm water.

[0024] The temperature of warm water to which the polyamide salt or polyamide salt mixture is added is suitably in the range of 60 to 95°C, and particularly preferably in the range of 70 to 90°C. In temperatures lower than 60°C, the dispersion of the polyamide salt or polyamide salt mixture is bad, and in temperatures higher than 95°C, there can be a case where the preparation of the antisetling agent is hindered due to foaming.

[0025] When the polyamide salt or polyamide salt mixture is added into warm water, it is generally dispersed immediately, but the stirring is continued at a temperature of 70 to 90°C for the order of 30 minutes to 1 hour for making the dispersion complete.

[0026] The thus obtained polyamide dispersion was cooled to a proper temperature in the range of 40 to 70°C, and transferred into a vessel in the state of liquid. When this dispersion is left alone at room temperature, it generally becomes a solid paste in the order of several hours to 1 day in the case where the rate of the polyamide in the additive is 20 % by weight.

[0027] For the purpose of the improvement of dispersibility in paints, the retainability of the luster of paint film, the dispersibility of the pigment, the defoaming properties of paints, the leveling of paint films at vertical plane, etc., a surfactant and/or various additives can be added to the antisetling agent for aqueous paints.

5 [0028] Paints suitable for the use of the antisetling agent for aqueous paints obtained in the invention are aqueous metallic paints and aqueous corrosion-resistant paints, wherein pigments having large particle sizes and large specific gravities, for example, aluminum pigments, pearlescent pigments such as mica, corrosion-resistant pigments, etc. are used, but in addition, the antisetling agent can also be applied to aqueous paints wherein general color pigments and/or extender pigments are used.

10 [0029] The time when the antisetling agent for aqueous paints of the invention is added to a paint may be the stage of kneading a pigment or may be after the preparation of a paint, and further it is also possible to make a masterbatch and add it. The addition temperature can be in the range of from room temperature to 80°C, and as dispersing machines, there can be used ones generally used in the preparation of paints.

[0030] The addition amount of the antisetling agent varies depending on the kind of paints and performance required thereon, but usually, the amount is suitably 0.25 to 5 % by weight, particularly preferably 0.5 to 3 % by weight in terms 15 of the polyamide based on the paint vehicle.

[0031] When the addition amount is smaller than 0.25 % by weight, settling-preventing effect is not sufficient, and when it is larger than 5 % by weight, there can be a case where bad influences such as the increase of the viscosity of the paint and the lowering of the luster thereof occur.

20 Effect of the Invention

[0032] By using the antisetling agent for aqueous paints of the invention, it is possible to prevent the settling of pigments having large particle sizes and large specific gravities, for example, aluminum pigments and pearlescent pigments such as mica used in aqueous metallic paints, corrosion-resistant pigments used in aqueous corrosion-resistant paints, and the preparation of paints having little lowering of the sharpness and/or water resistance of paint film is made possible.

[0033] The invention is further detailedly described below according to examples. "part" and "%" in the following show "weight part" and "% by weight", respectively.

30 Polyamide Synthesis Example 1

[0034] 283.2 Parts (0.48 mole) of a dimer acid (made by Henkel Japan Co., Ltd., trade name: Versadyme 228, which is the same hereinafter) and 56.6 parts (20 % of the total carboxylic acids, which is the same hereinafter) of xylene were put in a 1-liter four-necked flask equipped with a stirring apparatus, a thermoregulator, a diversion device and a nitrogen-introducing tube, and heated to 50°C to make a solution. Then, 19.2 parts (0.32 mole) of ethylenediamine 35 was added gradually, and the mixture was stirred at 130 to 140°C for 10 minutes. The mixture was further gradually heated to 175°C to carry out dehydration reaction. A palely brown polyamide (acid value: 64) obtained by 4 hours reaction was cooled up to 120°C, 28.5 parts (0.32 mole) of 2-dimethylaminoethanol and 145.4 parts (50 % of the polyamide, which is the same hereinafter) of propylene glycol monomethyl ether were added, and the mixture was 40 stirred at 85 to 95°C for 30 minutes. Thereafter, the mixture was once cooled to room temperature, and an antisetling agent for aqueous paints was prepared by a two-stage method.

Example 1

45 [0035] 136.1 Parts of deionized water was put in a 500-ml four-necked flask equipped with a stirring apparatus, a cooling pipe and a thermometer, and heated to 75°C. Separately, 63.9 parts of the above polyamide amine salt mixture was heated to 90°C to make it liquid, and gradually added into the above warm water under stirring. The polyamide amine salt mixture was immediately dispersed, but, for making the dispersion complete, the stirring was continued in the temperature range of 75 to 85°C for 30 minutes. After the completion of the dispersion, the mixture was cooled to 50 60°C, transferred into a vessel, and left alone at room temperature to give a desired antisetling agent for aqueous paints. This was a solid paste in observation after one day.

Polyamide Synthesis Examples 2 to 9

55 [0036] Polyamides were obtained according to the synthesis process of the Polyamide Synthesis Example 1, using the compounding ratios of Table-1, respectively.

Examples 2 to 10

[0037] Antisettling agents for aqueous paints were obtained using the same process as in Example 1 and the compounding ratios of Table-2, respectively.

Polyamide Synthesis Comparative Example 1

[0038] 283.2 Parts (0.48 mole) of the dimer acid and 56.6 parts of xylene were put in a 1-liter four-necked flask equipped with a stirring apparatus, a thermoregulator, a diversion device and a nitrogen-introducing tube, and heated to 50°C to make a solution. Then, 46.5 Parts (0.40 mole) of hexamethylenediamine melted with heating was added gradually, and the mixture was stirred at 130 to 140°C for 10 minutes. The mixture was gently heated up to 175°C to carry out dehydration reaction. A palely brown polyamide (acid value: 31) obtained by 4 hours reaction was cooled up to 120°C, 14.3 parts (0.16 mole) of 2-dimethylaminoethanol and 157.7 parts of propylene glycol monomethyl ether were added, and the mixture was stirred at 85 to 95°C for 30 minutes. Thereafter, the mixture was once cooled to room temperature, and an antisettling agent for aqueous paints was prepared by a two-stage method.

Comparative Example 1

[0039] 138.2 Parts of deionized water was put in a 500-ml four-necked flask equipped with a stirring apparatus, a cooling pipe and a thermometer, and heated to 75°C. Separately, 61.8 parts of the above polyamide amine salt mixture was heated to 90°C to make it liquid, and gradually added into the above warm water under stirring. After the completion of the addition, the stirring was continued in a temperature range of 75 to 85°C for 30 minutes. After the completion of the dispersion, the mixture was cooled to 60°C, transferred into a vessel, and left alone at room temperature. In observation after one day, this became ununiform because of the separation of the polyamide, and thus showed a state such that it could not be used as an antisettling agent for aqueous paints.

Polyamide Synthesis Comparative Example 2

[0040] A polyamide (acid value: 121) was obtained according to the synthetic process of Polyamide Synthesis Example 1 using 354.0 parts (0.60 mole) of the dimer acid, 24.4 parts (0.21 mole) of hexamethylenediamine and 70.8 parts of xylene. 69.5 Parts (0.78 mole) of 2-dimethylaminoethanol and 185.4 parts of propylene glycol monomethyl ether were added to this polyamide to give a polyamide amine salt mixture, and the mixture was once cooled to room temperature.

Comparative Example 2

[0041] An antisettling agent for comparison was obtained from 67.5 parts of the above polyamide amine salt mixture and 132.5 parts of deionized water according to the preparation process of Example 1.

Polyamide Synthesis Comparative Example 3

[0042] A polyamide (acid value: 157) was synthesized according to the synthetic process of Example 1 using 177.0 parts (0.30 mole) of the dimer acid, 131.7 parts (0.70 mole) of azelaic acid, 58.1 parts (0.50 mole) of hexamethylenediamine and 61.8 parts of xylene. While the temperature of this polyamide is maintained in the range of 125 to 135°C, 44.6 parts (0.50 mole) of 2-dimethylaminoethanol and 174.4 parts of propylene glycol monomethyl ether were added thereto, and the mixture was stirred in the same temperature range for 30 minutes (this polyamide amine salt mixture was solid at temperatures of 125°C or less). Then, this mixture was once cooled to room temperature.

Comparative Example 3

[0043] 134.9 Parts of deionized water was put in a 500-ml four-necked flask equipped with a stirring apparatus, a cooling pipe and a thermometer, and heated to 75°C. Separately, 65.1 parts of the above polyamide amine salt mixture was heated to 130°C to make it liquid, and gradually added into the above warm water under stirring. After the completion of the addition, the stirring was continued in a temperature range of 75 to 85°C for 30 minutes. After the completion of the dispersion, the mixture was cooled to 60°C, transferred into a vessel, and left alone at room temperature. In observation after one day, this was a fluid paste.

Polyamide Synthesis Comparative Example 4

[0044] 282.3 Parts (1.50 mole) of azelaic acid and 56.6 parts (20 % of azelaic acid) of xylene were put in a 1-liter four-necked flask equipped with a stirring apparatus, a thermoregulator, a diversion device and a nitrogen-introducing tube, and heated to 110°C to make a solution. Then, 104.6 Parts (0.90 mole) of hexamethylenediamine melted with heating was added gradually, and the mixture was gradually heated to 175°C to carry out dehydration reaction. A polyamide (acid value: 174) obtained by 4 hours reaction was once cooled to room temperature, and used for the preparation of an antisetling agent. In the case of this polyamide, it tended to be solid when neutralized with a neutralizing amine, and neutralization was made at the time of the preparation of an antisetling agent.

Comparative Example 4

[0045] 128.0 Parts of deionized water, 40.0 parts of the above polyamide, 12.0 parts of 2-dimethylaminoethanol and 20.0 parts of propylene glycol monomethyl ether were put in a 500-ml four-necked flask equipped with a stirring apparatus, a cooling pipe and a thermometer, and gradually heated under stirring. After dispersion was carried out at 95°C for 1 hour, the mixture was cooled up to 85°C, transferred into a vessel, and left alone at room temperature. In observation after one day, this was a solid paste.

Table-1 (Polyamide)

	Polyamide Synthesis Example										Polyamide Synthesis Comparative Example			
	1	2	3	4	5	6	7	8	9	10	1	2	3	4
Omer acid (mole)	0.48	0.50	0.50	0.50	0.48	0.57	0.63	0.48	0.44	0.60	0.48	0.60	0.30	
Dicarboxylic acid (mole)						0.18								
Azoic acid							0.27			0.15			0.70	1.50
Monocarboxylic acid (mole)								0.18						
12-Hydroxystearic acid									0.24	0.16				
Diamine (mole)	0.32				0.16			0.36						
Ethylenediamine		0.30			0.16	0.45	0.60		0.36	0.55	0.40	0.21	0.50	0.90
Hexamethylenediamine														
1, 12-Dodecanediamine			0.30											
4, 4'-Diaminodiphenylmethane				0.30										
2-Dimethylaminoethanol	0.32	0.40	0.40	0.40	0.32	0.60	0.60	0.42	0.40	0.56	0.16	0.78	0.50	-
Acid value of polyamide	64	75	70	72	63	84	73	65	55	60	31	121	157	174

[Note]

In all the Polyamide Synthesis Examples and Polyamide Synthesis Comparative Examples, xylene

(20 % of the total carboxylic acids) was used as a dehydration aid at the time of polyamide synthesis.

In all the Polyamide Synthesis Examples and Polyamide Synthesis Comparative Examples except

Polyamide Synthesis Comparative Example 4, propylene glycol monomethyl ether (50 % of the polyamide)

was used for the purpose of lowering the viscosity of the polyamide amine salt mixture.

Table-2

(Antisetling agent for aqueous paints)		
	Polyamide or polyamide amine salt mixture (weight part)	Deionized water (weight part)
Example 1	Polyamide amine salt mixture of Polyamide Synthesis Example 1 63.9	136.1
Example 2	Polyamide amine salt mixture of Polyamide Synthesis Example 2 64.5	135.5
Example 3	Polyamide amine salt mixture of Polyamide Synthesis Example 3 64.1	135.9
Example 4	Polyamide amine salt mixture of Polyamide Synthesis Example 4 64.2	135.8
Example 5	Polyamide amine salt mixture of Polyamide Synthesis Example 5 63.8	136.2
Example 6	Polyamide amine salt mixture of Polyamide Synthesis Example 6 65.3	134.7
Example 7	Polyamide amine salt mixture of Polyamide Synthesis Example 7 64.4	135.6
Example 8	Polyamide amine salt mixture of Polyamide Synthesis Example 8 64.8	135.2
Example 9	Polyamide amine salt mixture of Polyamide Synthesis Example 9 63.9	136.1
Example 10	Polyamide amine salt mixture of Polyamide Synthesis Example 10 64.2	135.8
Comparative Example 1	Polyamide amine salt mixture of Polyamide Synthesis Comparative Example 1 61.8	138.2
Comparative Example 2	Polyamide amine salt mixture of Polyamide Synthesis Comparative Example 2 67.5	132.5
Comparative Example 3	Polyamide amine salt mixture of Polyamide Synthesis Comparative Example 3 65.1	134.9
Comparative Example 4	Polyamide amine salt mixture of Polyamide Synthesis Comparative Example 4 40.0	128.0
[Note] In Comparative Example 4, 12.0 parts of 2-dimethylaminoethanol and 20.0 parts of propylene glycol monomethyl ether were added at the time of the preparation.		

Test example

[0046] Performance tests of the antisetling agents for aqueous paints were carried out on the aqueous acrylic melamine resin paint compositions of the following compositions (weight rates).

Coatex WF-268 (water soluble acrylic resin made by Toray Co., Ltd.)	44.1 parts
Cymel 370 (melamine resin made by Mitsui Cytec Co., Ltd.)	6.4 parts
Deionized water	49.5 parts
Inodin 504 (metallic pigment sold by Merck Japan Co., Ltd.)	5.0 parts
Antisetling agent for aqueous paints (one of the products of Examples, Comparative Examples and on the market)	2.0 parts

Method of the addition of an antissettling agent for aqueous paints:

- [0047] Coatax WF-268, Cymel 370 and deionized water are mixed under stirring to give a clear paint. Iriodin 504 and the antissettling agent for aqueous paints (in the blank test, Iriodin 504 alone) are added to this, and dispersed by a T.K. autohomomixer (made by Tokushu Kika Kogyo Co., Ltd., type M, diameter of the blade: 4cm) (2,000 rpm x 15 minutes).

Viscosity and TI value:

- [0048] The viscosities (CPS) at 25°C and 60 rpm and at 25°C and 6 rpm of the resultant paint are measured using a B-type viscometer, and the ratio (viscosity at 6 rpm/viscosity at 60 rpm) is calculated. The larger the value of the ratio (TI value) is, the larger the thixotropy is.

Settling-preventing properties

- [0049] The paint is diluted with deionized water so that the viscosity measured using a Ford cup #4 may be 40 seconds (25°C), the diluted paint is transferred into a 250-ml glass bottle, and the percentage of the volume of the Iriodin which settled to the volume of the whole paint is measured.

- [0050] The test results are shown in Table-3. From the results of Table-3, it is understood that when the antissettling agent for aqueous paints of the invention is added to the aqueous metallic paint, it exerts an excellent effect in the prevention of the settling of the metallic pigment.

Table-3

Antissettling agent for aqueous paints	(Performance tests)			
	Before dilution		Settling-preventing properties (%)	
	60 rpm	TI value	3 days later	10 days later
Blank	230	0.95	12.7	10.8
Example 1	438	1.60	99.4	88.5
Example 2	726	2.12	99.4	94.0
Example 3	966	2.65	100	97.1
Example 4	386	1.24	99.7	98.2
Example 5	260	1.15	94.5	31.5
Example 6	714	1.71	100	97.6
Example 7	768	2.01	100	100
Example 8	650	1.38	99.4	80.9
Example 9	460	1.85	61.0	49.4
Example 10	632	1.94	98.8	94.3
Comparative Example 2	-	-	-	-
Comparative Example 3	151	0.96	18.1	15.0
Comparative Example 4	455	1.05	19.8	16.7
Product on the market	349	0.96	15.6	15.6
[Note] As to Comparative Example 1, since the state was ununiform, the tests were not carried out, and as to Comparative Example 2, since the paint composition became a gel showing roping properties, the tests were stopped. The product on the market is Rheolate 2,000 made by Rheox Co.				

Claims

1. An antisetling agent for aqueous paints obtained by neutralizing a polyamide having an acid value in the range of 30 to 120, which is obtained by reacting a primary diamine having 2 to 12 carbon atoms with a dimer dicarboxylic acid obtained by polymerizing an unsaturated fatty acid (common name: dimer acid) in a mole ratio of the total carboxylic acids to the primary diamine being 5:4 - 2:1 or a mixture of a dimer acid with another dicarboxylic acid having 3 to 21 carbon atoms and/or a monocarboxylic acid having 2 to 22 carbon atoms in which the mole ratio of the dimer acid to the total carboxylic acids is 50% or more, with a neutralizing base, and then dispersing the neutralized polyamide in a medium mainly composed of water.
2. The antisetling agent for aqueous paints according to claim 1 wherein the mole ratio of the total carboxylic acids to the primary diamine is in the range of 5:4 to 2:1.
3. The antisetling agent for aqueous paints according to claim 1 wherein the mole ratio of the dimer acid contained in the total carboxylic acids is 50 mol % or more.
4. The antisetling agent for aqueous paints according to claim 1 wherein the acid value of the polyamide obtained by reacting the total carboxylic acids with the primary diamine is in the range of 30 to 120.
5. The antisetling agent for aqueous paints according to claim 1 wherein the primary diamine is ethylenediamine, 1,4-diaminobutane, hexamethylenediamine, 1,10-decamethylenediamine, 1,11-undecamethylenediamine, 1,12-dodecamethylenediamine, xylylenediamine or 4,4'-diaminodiphenylmethane.
6. The antisetling agent for aqueous paints according to claim 1 wherein the dicarboxylic acid is succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, dodecanedioic acid or isophthalic acid.
7. The antisetling agent for aqueous paints according to claim 1 wherein the monocarboxylic acid is acetic acid, butyric acid, caproic acid, caprylic acid, capric acid, lauric acid, myristic acid, palmitic acid, stearic acid, behenic acid, 12-hydroxystearic acid or oleic acid.

Patentansprüche

1. Anti-Absetzmittel für wässrige Anstrichmittel, erhalten durch Neutralisation eines Polyamids mit einer Säurezahl im Bereich von 30 bis 120, welches durch Umsetzung eines primären Diamins mit 2 bis 12 Kohlenstoffatomen mit einer dimeren Dicarbonsäure, erhalten durch Polymerisation einer ungesättigten Fettsäure (Trivialname: Dimer-säure) in einem Molverhältnis von Gesamtcarbonsäuren zu primärem Amin von 5:4 - 2:1 oder aus einem Gemisch einer Dimersäure mit einer anderen Dicarbonsäure mit 3 bis 21 Kohlenstoffatomen und/oder einer Monocarbonsäure mit 2 bis 22 Kohlenstoffatomen, wobei das Molverhältnis der Dimersäure zu den Gesamtcarbonsäuren 50% oder mehr beträgt, erhalten worden ist, mit einer Neutralisationsbase und dann Dispersion des neutralisierten Polyamids in einem Medium, das hauptsächlich aus Wasser besteht.
2. Anti-Absetzmittel für wässrige Anstrichmittel nach Anspruch 1, wobei das Molverhältnis der Gesamtcarbonsäuren zu dem primären Diamin im Bereich von 5:4 bis 2:1 liegt.
3. Anti-Absetzmittel für wässrige Anstrichmittel nach Anspruch 1, wobei das Molverhältnis der Dimersäure, die in den Gesamtcarbonsäuren enthalten ist, 50 Mol-% oder mehr beträgt.
4. Anti-Absetzmittel für wässrige Anstrichmittel nach Anspruch 1, wobei die Säurezahl des Polyamids, erhalten durch Umsetzung der Gesamtcarbonsäuren mit dem primären Diamin, im Bereich von 30 bis 120 liegt.
5. Anti-Absetzmittel für wässrige Anstrichmittel nach Anspruch 1, wobei das primäre Amin Ethylendiamin, 1,4-Diaminobutan, Hexamethyldiamin, 1,10-Decamethyldiamin, 1,11-Undecamethyldiamin, 1,12-Dodecamethyldiamin, Xylyldiamin oder 4,4'-Diamindiphenylmethan ist.
6. Anti-Absetzmittel für wässrige Anstrichmittel nach Anspruch 1, wobei die Dicarbonsäure Bernsteinsäure, Glutarsäure, Adipinsäure, Pimelinsäure, Suberinsäure, Azelainsäure, Sebacinsäure, Dodecandinsäure oder Isophthal-säure ist.

7. Anti-Absetzmittel für wässrige Anstrichmittel nach Anspruch 1, wobei die Monocarbonsäure Essigsäure, Buttersäure, Capronsäure, Caprylsäure, Caprinsäure, Laurinsäure, Myristinsäure, Palmitinsäure, Stearinsäure, Behensäure, 12-Hydroxystearinsäure oder Ölsäure ist.

5

Revendications

1. Agent anti-sédimentation pour peintures aqueuses, obtenu en neutralisant un polyamide ayant un indice d'acide compris dans l'intervalle de 30 à 120, qui est obtenu en faisant réagir une diamine primaire ayant 2 à 12 atomes de carbone avec un acide dicarboxylique dimère obtenu en polymérisant un acide gras insaturé (nom commun : acide dimère) en un rapport molaire des acides carboxyliques totaux à la diamine primaire de 5:4 à 2:1 ou un mélange d'un acide dimère avec un autre acide dicarboxylique ayant 3 à 21 atomes de carbone et/ou un acide monocarboxylique ayant 2 à 22 atomes de carbone dans lequel la proportion molaire de l'acide dimère par rapport aux acides carboxyliques totaux est de 50 % ou plus, avec une base neutralisante, puis en dispersant le polyamide neutralisé dans un milieu consistant principalement en eau.
2. Agent anti-sédimentation pour peintures aqueuses selon la revendication 1, dans lequel le rapport molaire des acides carboxyliques totaux à la diamine primaire est compris dans l'intervalle de 5:4 à 2:1.
3. Agent anti-sédimentation pour peintures aqueuses selon la revendication 1, dans lequel la proportion molaire de l'acide dimère contenu dans les acides carboxyliques totaux est de 50 mol % ou plus.
4. Agent anti-sédimentation pour peintures aqueuses selon la revendication 1, dans lequel l'indice d'acide du polyamide obtenu en faisant réagir les acides carboxyliques totaux avec la diamine primaire se situe dans l'intervalle de 30 à 120.
5. Agent anti-sédimentation pour peintures aqueuses selon la revendication 1, dans lequel la diamine primaire est l'éthylènediamine, le 1,4-diaminobutane, l'hexaméthylènediamine, la 1,10-décaméthylènediamine, la 1,11-undécaméthylènediamine, la 1,12-dodécaméthylènediamine, la xylylènediamine ou le 4,4'-diaminodiphénylméthane.
6. Agent anti-sédimentation pour peintures aqueuses selon la revendication 1, dans lequel l'acide dicarboxylique est l'acide succinique, l'acide glutarique, l'acide adipique, l'acide pimélique, l'acide subérique, l'acide azélaïque, l'acide sébacique, l'acide dodécanedioïque ou l'acide isophtalique.
7. Agent anti-sédimentation pour peintures aqueuses selon la revendication 1, dans lequel l'acide monocarboxylique est l'acide acétique, l'acide butyrique, l'acide caproïque, l'acide caprylique, l'acide caprique, l'acide laurique, l'acide myristique, l'acide palmitique, l'acide stéarique, l'acide béhénique, l'acide 12-hydroxystéarique ou l'acide oléique.

40

45

50

55

2/9/1

DIALOG(R)File 351:Derwent WPI

(c) 2003 Thomson Derwent. All rts. reserv.

012141456

WPI Acc No: 1998-558368/199848

XRAM Acc No: C98-167248

Sun protection formulation forming fine stable emulsion with good water resistance and skin cosmetic compatibility - contains chitosan, oil, emulsifier and ultraviolet light filter

Patent Assignee: HENKEL KGAA (HENK); COGNIS DEUT GMBH (COGN-N)

Inventor: ANSMANN A; KUEHNE S; WACHTER R

Number of Countries: 024 Number of Patents: 003

Patent Family:

Patent No	Kind	Date	Applicat No	Kind	Date	Week
DE 19716070	A1	19981022	DE 1016070	A	19970417	199848 B
EP 879592	A2	19981125	EP 98106471	A	19980408	199851
DE 19716070	C2	20000824	DE 1016070	A	19970417	200041

Priority Applications (No Type Date): DE 1016070 A 19970417

Patent Details:

Patent No	Kind	Lan	Pg	Main IPC	Filing Notes
-----------	------	-----	----	----------	--------------

DE 19716070	A1		7	A61K-007/42	
-------------	----	--	---	-------------	--

EP 879592	A2 G			A61K-007/42	
-----------	------	--	--	-------------	--

Designated States (Regional): AL AT BE CH DE DK ES FI FR GB GR IE IT LI

LT LU LV MC MK NL PT RO SE SI

DE 19716070	C2			A61K-007/42	
-------------	----	--	--	-------------	--

Abstract (Basic): DE 19716070 A

Sun protection formulation contains (a) oil, (b) emulsifier, (c) chitosan and (d) UV light filter.

Also claimed is the use of cationic biopolymers as water repellents for the production of sun protection agents.

ADVANTAGE - Phase separation tends to occur with oils and emulsions containing large amounts of UV filter. In addition, chemical reactions between many UV filters and other components reduce the storage stability. Consumers require transparent formulations with high skin cosmetic compatibility, even on very sensitive skin, and also high enough water resistance to eliminate the need for re-application after bathing. Chitosans stabilise emulsions, so that finely-divided formulations are obtained, which have excellent storage stability, even at temperatures above 50 deg. C. They are also extremely resistant to water. The formulations have high skin cosmetic compatibility.

Dwg.0/0

Title Terms: SUN; PROTECT; FORMULATION; FORMING; FINE; STABILISED; EMULSION; WATER; RESISTANCE; SKIN; COSMETIC; COMPATIBLE; CONTAIN; CHITOSAN; OIL; EMULSION; ULTRAVIOLET; LIGHT; FILTER

Derwent Class: A96; D21; E19

International Patent Class (Main): A61K-007/42

International Patent Class (Additional): A61K-007/48

File Segment: CPI

Manual Codes (CPI/A-N): A10-E09; A12-V04C; D08-B09A; E05-E03; E05-G09C;

E05-G09D; E06-D05; E07-A02D; E07-A02H; E10-A07; E10-A22; E10-B02A;

E10-C03; E10-C04C; E10-E04; E10-F02A1; E10-F02A2; E10-G02G1; E10-H01D;

E31-P05; E34; E35

Chemical Fragment Codes (M3):

01 G011 G012 G013 G019 G100 H401 H481 H5 H541 H542 H581 H582 H583 H584
H589 H8 J011 J012 J271 J272 M220 M221 M222 M223 M224 M225 M226 M231
M232 M233 M240 M262 M272 M281 M282 M312 M313 M321 M322 M323 M331
M332 M342 M383 M392 M393 M414 M416 M510 M520 M530 M531 M532 M540
M620 M782 M903 M904 Q130 Q254 Q263 Q623 R022 9848-ANZ01-K
9848-ANZ01-M

02 H4 H401 H402 H481 H482 H581 H582 H583 H584 H589 H714 H721 H722 H8 J0
J011 J012 J2 J271 J272 M210 M215 M216 M220 M221 M222 M223 M224 M225
M226 M231 M232 M233 M262 M281 M282 M312 M313 M321 M322 M323 M332
M342 M343 M383 M391 M392 M393 M416 M620 M782 M903 M904 Q130 Q254
Q263 Q623 R022 9848-ANZ02-K 9848-ANZ02-M

03 F012 F013 F014 F113 H4 H402 H403 H421 H422 H481 H482 H483 H521 H522
H581 H582 H583 H584 H589 H714 H721 H722 H8 J0 J011 J012 J2 J221 J271
J272 K0 L8 L810 L821 L831 M210 M215 M216 M220 M221 M222 M223 M224
M225 M226 M231 M232 M233 M262 M281 M282 M312 M321 M322 M323 M332
M342 M343 M373 M383 M391 M392 M393 M413 M510 M521 M530 M540 M782
M903 M904 Q130 Q254 Q263 Q623 R022 9848-ANZ03-K 9848-ANZ03-M

04 F012 F013 F014 F015 F016 F019 F113 F123 F199 H4 H403 H404 H405 H422
H423 H424 H481 H482 H483 H5 H521 H522 H523 H581 H582 H583 H584 H589
H8 K0 L8 L810 L821 L822 L823 L824 L831 M126 M129 M141 M149 M220 M221
M222 M223 M224 M225 M226 M231 M232 M233 M272 M281 M311 M312 M321
M322 M323 M332 M342 M373 M383 M391 M392 M393 M413 M510 M521 M522
M523 M530 M540 M782 M903 M904 Q130 Q254 Q263 Q623 R022 9848-ANZ04-K
9848-ANZ04-M

05 H401 H402 H403 H404 H481 H482 H483 H484 H714 H721 H722 H723 J0 J011
J012 J013 J014 J2 J271 J272 J273 L630 L660 M210 M211 M212 M213 M214
M215 M216 M220 M221 M222 M223 M224 M225 M226 M231 M232 M233 M262
M280 M281 M282 M283 M311 M312 M313 M314 M315 M316 M321 M322 M323
M331 M332 M333 M334 M340 M342 M343 M381 M383 M391 M392 M393 M416
M620 M782 M903 M904 Q130 Q254 Q263 Q623 R022 9848-ANZ05-K
9848-ANZ05-M

06 F012 F013 F014 F015 F016 F019 F113 F123 F199 H4 H401 H402 H403 H404
H405 H421 H422 H423 H424 H481 H482 H483 H484 H521 H581 H714 H721
H722 H723 H8 J0 J011 J012 J013 J014 J2 J221 J222 J271 J272 J273 L810
L821 L822 L823 L824 L831 M126 M141 M210 M211 M212 M213 M214 M215
M216 M220 M221 M222 M223 M224 M225 M226 M231 M232 M233 M262 M280
M281 M282 M283 M311 M315 M316 M321 M322 M331 M332 M334 M342 M344
M373 M381 M383 M391 M392 M413 M416 M510 M520 M521 M522 M530 M540
M620 M782 M903 M904 Q130 Q254 Q263 Q623 R022 9848-ANZ06-K
9848-ANZ06-M

07 B415 B701 B713 B720 B815 B831 H581 H582 H583 H584 H589 M210 M211
M212 M213 M214 M215 M216 M220 M221 M222 M223 M224 M225 M226 M231
M232 M233 M272 M281 M282 M283 M312 M320 M321 M322 M323 M332 M342
M383 M391 M392 M393 M411 M510 M520 M530 M540 M620 M782 M903 M904
Q130 Q254 Q263 Q623 R022 9848-ANZ07-K 9848-ANZ07-M

08 F012 F013 F014 F015 F016 F019 F123 F199 H401 H402 H403 H404 H405
H422 H424 H481 H482 H483 H484 H521 H522 H523 H581 H583 H713 H714
H716 H721 H722 H723 J0 J011 J013 J014 J171 J172 J173 J2 J221 J222
J271 J272 J273 L660 L699 L810 L821 L831 M210 M211 M212 M213 M214
M215 M216 M220 M221 M222 M223 M224 M225 M226 M231 M232 M233 M262
M272 M280 M281 M282 M283 M311 M312 M313 M314 M315 M316 M320 M321
M322 M323 M331 M332 M333 M334 M340 M342 M344 M349 M373 M381 M383
M391 M392 M393 M413 M416 M510 M520 M521 M522 M523 M530 M540 M620
M782 M903 M904 Q130 Q254 Q263 Q623 R022 9848-ANZ08-K 9848-ANZ08-M

09 G010 G011 G013 G100 H100 H141 H401 H441 H541 H721 J0 J011 J131 J171
J231 J271 M210 M211 M212 M213 M214 M215 M216 M220 M221 M222 M223
M224 M225 M226 M231 M232 M233 M272 M280 M281 M282 M312 M320 M321

M332 M342 M372 M391 M414 M510 M520 M531 M540 M782 M903 M904 Q130
 Q254 Q263 R022 9848-ANZ09-K 9848-ANZ09-M
 10 G010 G011 G012 G013 G014 G015 G016 G017 G018 G019 G100 J5 J581 M1
 M121 M131 M150 M210 M211 M212 M213 M214 M215 M216 M220 M221 M222
 M223 M224 M225 M226 M231 M232 M233 M240 M280 M281 M282 M283 M320
 M414 M510 M520 M532 M540 M782 M903 M904 Q130 Q254 Q263 R022
 9848-ANZ10-K 9848-ANZ10-M
 11 G010 G011 G012 G013 G014 G015 G016 G017 G018 G019 G100 H541 J5 J582
 M1 M121 M135 M210 M211 M212 M213 M214 M215 M216 M220 M221 M222 M223
 M224 M225 M226 M231 M232 M233 M240 M272 M280 M281 M282 M283 M311
 M321 M342 M382 M391 M414 M510 M520 M532 M540 M782 M903 M904 Q130
 Q254 Q263 R022 9848-ANZ11-K 9848-ANZ11-M
 12 G013 G031 G036 G038 G060 G111 G623 H7 H720 J5 J561 M1 M123 M132 M210
 M211 M240 M283 M311 M321 M343 M414 M510 M520 M531 M541 M782 M903
 M904 Q130 Q254 Q263 R022 9848-ANZ12-K 9848-ANZ12-M
 13 H1 H181 J0 J011 J1 J171 K0 L7 L722 M210 M211 M273 M283 M311 M321
 M342 M349 M381 M391 M416 M620 M782 M903 M904 M910 Q130 Q254 Q263
 Q623 R022 R00829-K R00829-M
 14 H4 H402 H482 H5 H589 H8 M280 M312 M313 M314 M315 M316 M323 M331 M332
 M333 M342 M383 M393 M620 M782 M903 M904 Q130 Q254 Q263 Q623 R022
 R90114-K R90114-M
 15 A313 A940 A960 C710 C730 M411 M417 M782 M903 M904 Q130 Q254 Q263
 R022 R10662-K R10662-M
 16 A313 A940 C108 C550 C730 C801 C802 C803 C804 C805 C807 M411 M782
 M903 M904 M910 Q130 Q254 Q263 R022 R01544-K R01544-M
 17 A256 A940 C108 C316 C540 C730 C801 C802 C803 C804 C805 M411 M782
 M903 M904 M910 Q130 Q254 Q263 R022 R01739-K R01739-M
 18 A758 A940 A960 A970 C710 C730 M411 M417 M782 M903 M904 Q130 Q254
 Q263 R022 R10427-K R10427-M
 19 A758 A940 C108 C550 C730 C801 C802 C803 C804 C805 C807 M411 M782
 M903 M904 Q130 Q254 Q263 R022 R06210-K R06210-M
 20 A426 A940 A960 C710 C730 M411 M417 M782 M903 M904 Q130 Q254 Q263
 R022 R07107-K R07107-M
 21 A426 A940 C108 C550 C730 C801 C802 C803 C804 C805 C807 M411 M782
 M903 M904 Q130 Q254 Q263 R022 R03239-K R03239-M
 22 A212 A940 B114 B701 B712 B720 B831 C108 C802 C803 C804 C805 C807
 M411 M782 M903 M904 M910 Q130 Q254 Q263 R022 R01541-K R01541-M
 23 G013 G031 G034 G038 G060 G111 G623 H7 H720 M1 M123 M132 M210 M211
 M240 M283 M311 M321 M343 M414 M510 M520 M531 M541 M610 M782 M903
 M904 Q130 Q254 Q263 R022 R11332-K R11332-M
 24 D012 D022 D711 G010 G100 K0 K4 K431 M1 M113 M280 M320 M412 M511 M520
 M531 M540 M782 M903 M904 Q130 Q254 Q263 R022 R04948-K R04948-M
 25 B114 B701 B712 B720 B831 C101 C108 C800 C802 C804 C805 C807 M411
 M782 M903 M904 Q130 Q254 Q263 R022 R06012-K R06012-M
 26 A422 A940 C108 C550 C730 C801 C802 C803 C804 C805 C807 M411 M782
 M903 M904 M910 Q130 Q254 Q263 R022 R01966-K R01966-M
 27 A422 A940 A960 C710 C730 M411 M417 M782 M903 M904 Q130 Q254 Q263
 R022 R19161-K R19161-M
 28 A430 C710 C810 M411 M417 M782 M903 M904 Q130 Q254 Q263 R022 R06421-K
 R06421-M
 29 A430 A940 C108 C550 C730 C801 C802 C803 C804 C805 C807 M411 M782
 M903 M904 M910 Q130 Q254 Q263 R022 R01520-K R01520-M
 30 A540 A940 A960 C710 C730 M411 M417 M782 M903 M904 Q130 Q254 Q263
 R022 R20698-K R20698-M
 31 A540 A940 C108 C550 C730 C801 C802 C803 C804 C805 C807 M411 M782
 M903 M904 M910 Q130 Q254 Q263 R022 R01521-K R01521-M

Polymer Indexing (PS):

<01>
 001 018; P1445-R F81 Si 4A; S9999 S1376
 002 018; ND01; K9643 K9621; B9999 B3418-R B3372; Q9999 Q9176 Q9165;
 K9847-R K9790

<02>
 001 018; R03882 D01 D11 D10 D23 D22 D31 D42 D50 D76 D86 F08 F07 F24 F28
 F26 F34 H0293 P0599 G3623 M2313
 002 018; ND01; K9643 K9621; B9999 B3418-R B3372; Q9999 Q9176 Q9165;
 K9847-R K9790

<03>
 001 018; H0000; M9999 M2153-R; M9999 M2777; P0055; H0226; P0975-R P0964
 F34 D01 D10
 002 018; ND01; K9643 K9621; B9999 B3418-R B3372; Q9999 Q9176 Q9165;
 K9847-R K9790
 003 018; Si 4A; H0157
 004 018; H0226

<04>
 001 018; P1445-R F81 Si 4A; M9999 M2153-R; H0226; M9999 M2459
 002 018; ND01; K9643 K9621; B9999 B3418-R B3372; Q9999 Q9176 Q9165;
 K9847-R K9790
 003 018; H0157
 004 018; H0226

<05>
 001 018; P8004 P0975 P0964 D01 D10 D11 D50 D82 F34; M9999 M2153-R;
 M9999 M2186; M9999 M2460
 002 018; ND01; K9643 K9621; B9999 B3418-R B3372; Q9999 Q9176 Q9165;
 K9847-R K9790
 003 018; P- 5A; H0157

<06>
 001 018; R00113 G1070 G0997 D01 D11 D10 D50 D83 F29 F26; H0000; P0055;
 P0975-R P0964 F34 D01 D10; P8004 P0975 P0964 D01 D10 D11 D50 D82
 F34; M9999 M2153-R; M9999 M2186; M9999 M2200; M9999 M2813
 002 018; D11 D10 D82 D83; H0237-R; P0055; P0975-R P0964 F34 D01 D10;
 M9999 M2153-R; M9999 M2186; M9999 M2200; M9999 M2813
 003 018; ND01; K9643 K9621; B9999 B3418-R B3372; Q9999 Q9176 Q9165;
 K9847-R K9790

Derwent Registry Numbers: 0829-U; 1506-U; 1508-U; 1520-U; 1521-U; 1541-U;
 1544-U; 1739-U; 1966-U

Specific Compound Numbers: R00829-K; R00829-M; R90114-K; R90114-M; R10662-K
 ; R10662-M; R01544-K; R01544-M; R01739-K; R01739-M; R10427-K; R10427-M;
 R06210-K; R06210-M; R07107-K; R07107-M; R03239-K; R03239-M; R01541-K;
 R01541-M; R11332-K; R11332-M; R04948-K; R04948-M; R06012-K; R06012-M;
 R01966-K; R01966-M; R19161-K; R19161-M; R06421-K; R06421-M; R01520-K;
 R01520-M; R20698-K; R20698-M; R01521-K; R01521-M

Generic Compound Numbers: 9848-ANZ01-K; 9848-ANZ01-M; 9848-ANZ02-K;
 9848-ANZ02-M; 9848-ANZ03-K; 9848-ANZ03-M; 9848-ANZ04-K; 9848-ANZ04-M;
 9848-ANZ05-K; 9848-ANZ05-M; 9848-ANZ06-K; 9848-ANZ06-M; 9848-ANZ07-K;
 9848-ANZ07-M; 9848-ANZ08-K; 9848-ANZ08-M; 9848-ANZ09-K; 9848-ANZ09-M;
 9848-ANZ10-K; 9848-ANZ10-M; 9848-ANZ11-K; 9848-ANZ11-M; 9848-ANZ12-K;
 9848-ANZ12-M